

Dry-shake Colored Aggregate Terrazzo

1. Concrete Pouring

Pour concrete according to the design specifications, achieving a level of ± 0 . The concrete grade shall not be less than C25. The thickness shall be at least 8 cm. Spread terrazzo aggregate at a rate of no less than 10 kg per square meter.

2. First Material Spreading

Spread half of the specified quantity of terrazzo material evenly over the freshly poured, just-set concrete surface.

3. First Slurry Extraction

Once the terrazzo material has absorbed some moisture, use a mechanical trowel to perform slurry extraction and level the surface with a straightedge.

4. Second Material Spreading

When the terrazzo material has hardened to a certain stage, spread the remaining half of the specified quantity of terrazzo material.

5. Second Slurry Extraction

After the terrazzo material has absorbed some moisture, use a mechanical trowel to perform slurry extraction and level the surface with a straightedge.

6. Mechanical Trowel Finishing

Based on the hardening of the floor, use a mechanical trowel to finish the surface.

7.Curing

After finishing, apply film curing or use a recommended curing agent.

8.Curing, Grinding, and Polishing

After 28 days, start surface grinding and apply curing agent, polishing up to 2000 grit.